
DURA+SKRIM® R20BV





PRODUCT DESCRIPTION

DURA SKRIM® R20BV consist of two sheets of high-strength virgin polyethylene film laminated together with a third layer of molten polyethylene. The black outer layers contain carbon black to enhance outdoor life. A durable scrim reinforcement placed between these plies greatly enhances tear resistance and increases service life.



DURA SKRIM® R20BV is reinforced with a high strength scrim reinforcement laid in a diagonal pattern spaced 3/8" apart for uniform tear resistance in both machine and transverse directions with an additional machine direction scrim every 3" across the width for increased stability.

PRODUCT USE

DURA SKRIM® R20BV is used in more demanding applications requiring high tear and puncture resistance and is designed to withstand longer-term outdoor applications requiring up to 10 years of exposure depending upon geographical locations.

DURA SKRIM® R20BV are designed to meet the requirements of the Geosynthetics Research Institute; GRI-GM22 Standard Specification.

SIZE & PACKAGING

DURA SKRIM® R20BV is available in a variety of widths and fabricated panels up to 80,000 square feet. All panels are manufactured in a quality controlled environment and are accordion folded and tightly rolled on a heavy-duty core for ease of handling and time-saving installation.





Temporary Rain Shed Cover

| PRODUCT | PART # |
|---------|--------|
|---------|--------|

APPLICATIONS

Modular Tank Liners Interim Landfill Caps

Evaporation Covers Remediation Covers

Remediation Liners Erosion Control Covers

Earthen Liners



FOUR-LAYER REINFORCED EXTRUSION LAMINATE - MEETS GRI-GM22

| | | DURA♦SKRIM R20BV | | | | |
|--------------------------------------|-------------|--|---------------------|-----------------|-----------------------------|--|
| | | IMPERIAL | | METRIC | | |
| PROPERTIES | TEST METHOD | MINIMUM | TYPICAL | MINIMUM | TYPICAL | |
| Appearance | | Black/Black | | | | |
| THICKNESS | ASTM D5199 | 17 Mil Average | 20 Mil Nominal | 0.43 mm Average | 0.51 mm Nominal | |
| WEIGHT | ASTM D751 | 94 lbs/MSF | 97 lbs/MSF | 459 g/m² | 474 g/m² | |
| Construction | | Extrusion laminated with scrim reinforcement | | | | |
| ² Grab Tensile | ASTM D7004 | 114 lbs | 138 lbs | 507 N | 614 N | |
| ² Grab Tensile Elongation | ASTM D7004 | 15 % | 17 % | 15 % | 17 % | |
| ³ TONGUE TEAR | ASTM D5884 | 53 lbs | 58 lbs | 236 N | 258 N | |
| CBR Puncture Resistance | ASTM D6241 | 320 lbs | 350 lbs | 1423 N | 1557 N | |
| Mullen Burst | ASTM D751 | 130 psi | 160 psi | 896 kPa | 1103 kPa | |
| HIGH PRESSURE OIT | ASTM D5885 | 1000 min | 2600 min | 1000 min | 2600 min | |
| WVTR | ASTM E96 | N/A | 0.009 grains/ft²•hr | N/A | 0.151 g/m ² •day | |
| Perm Rating | ASTM E96 | N/A | 0.022 Perms | N/A | 0.0145 g/m²•day•mm Hg | |
| Hydraulic Conductivity | ASTM E96 | 1.77x10 ⁻¹⁰ cm/sec | | | | |
| MAXIMUM STATIC USE TEMPERA- | | 180° F | | 82° C | | |
| MINIMUM STATIC USE TEMPERA- | | -70° F -57° C | | ° C | | |
| Low Temperature Bend Test | ASTM D2136 | -70° F | | | | |

² Tests are an average of primary reinforcement directions.

³ Tests are an average of machine and transverse directions.



DURA SKRIM® R20BV consist of two sheets of high-strength virgin polyethylene film laminated together with a third layer of molten polyethylene. The black outer layers contain carbon black to enhance outdoor life. A durable scrim reinforcement placed between these plies greatly enhances tear resistance and increases service life. DURA SKRIM® R20BV is reinforced with a high strength scrim reinforcement laid in a diagonal pattern spaced 3/8" apart for uniform tear resistance in both machine and transverse directions with an additional machine direction scrim every 3" across the width for increased stability.



Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. VIAFLEX MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.viaflex.com

VIAFLEX, INC.

