

# DURA♦SKRIM® N60B

SCRIM REINFORCED POLYETHYLENE – NSF/ANSI STANDARD 61 CERTIFIED

## PRODUCT DESCRIPTION

DURA♦SKRIM® N60B is a flexible geomembrane, reinforced with a closely knit 9x9 weft inserted polyester scrim fully encapsulated between two layers of highly UV stabilized linear low density polyethylene. Exceptional toughness, high tensile and puncture strength is achieved with the combination of premium high strength LLDPE and dense scrim reinforcement. A highly stabilized formulation consisting of antioxidants, UV stabilizers and carbon black provide excellent protection for long-term exposed or barrier applications. DURA♦SKRIM® N-Series geomembranes are produced in the color black as standard, and are available in other custom manufactured colors with minimum order quantity requirements.

## PRODUCT USE

DURA♦SKRIM® N60B is used in applications that require exceptional outdoor life requiring up to 20 years of exposure depending upon the geographical location. Applications requiring high tear properties, exceptional tensile strength and puncture resistance utilize N60B to meet these demands. DURA♦SKRIM® N-Series is manufactured from a chemical-resistant, linear-low-density polyethylene with excellent cold crack performance and resistance to thermal expansion.

DURA♦SKRIM® N60B meets the physical property values as stated in GRI test method GM25 Category 1, and is certified under the NSF/ANSI Standard 61, Drinking Water System

## SIZE & PACKAGING

DURA♦SKRIM® N60B is available in a variety of widths and lengths to meet the project requirements. Large diameter mill rolls are available to assure an efficient seaming process. Factory welded panels are produced in a controlled environment and are accordion folded and tightly rolled on a heavy-duty core for ease of handling and time saving installation.

# DURA♦SKRIM®



Bio Cell Liner

## PRODUCT

## PART #

DURA♦SKRIM ..... N60B

## APPLICATIONS

- |                         |                         |
|-------------------------|-------------------------|
| Waste Lagoon Liners     | Landfill Caps           |
| Floating Covers         | Erosion Control Covers  |
| Daily Landfill Covers   | Canal Liners            |
| Modular Tank Liners     | Disposal Pit Liner      |
| Tunnel Liners           | Water Containment Ponds |
| Remediation Liners      | Heap Leach Liner        |
| Earthen Liners          | Secondary Containment   |
| Interim Landfill Covers | Remediation Covers      |

# DURA♦SKRIM® N60B

SCRIM REINFORCED POLYETHYLENE – NSF/ANSI STANDARD 61 CERTIFIED

PRO-FORMA DATA SHEET

		DURA♦SKRIM® N60B			
		IMPERIAL		METRIC	
PROPERTIES	TEST METHOD	MINIMUM	TYPICAL	MINIMUM	TYPICAL
APPEARANCE		Black		Black	
CORE THICKNESS	ASTM D5199	54 mil	60 mil	1.44 mm	1.52 mm
WEIGHT	ASTM D751	250 lbf/msf	262 lbf/msf	1020 g/m <sup>2</sup>	1069 g/m <sup>2</sup>
CONSTRUCTION		9x9-1000 Denier PET scrim reinforced polyethylene			
TONGUE TEAR STRENGTH	ASTM D5884	120 lbf	135 lbf	534 N	600 N
GRAB TENSILE AT BREAK	ASTM D7004	330 lbf	360 lbf	1468 N	1602 N
TENSILE ELONGATION AT BREAK	ASTM D7004	22 %	30 %	22 %	30 %
PUNCTURE RESISTANCE	ASTM D4833	120 lbf	135 lbf	533 N	600 N
STANDARD OIT OR HIGH PRESSURE HPOIT	ASTM D3895 ASTM D5885	100 min 400 min	150 min 2400 min	100 min 400 min	150 min 2400 min
HYDRAULIC CONDUCTIVITY		1.47 x 10 <sup>-10</sup> cm/sec			
MAXIMUM STATIC USE TEMPERATURE		180° F		82° C	
MINIMUM STATIC USE TEMPERATURE		-70° F		-57° C	

PRO-FORMA SHEET CONTENTS: The data listed in the Pro-Forma data sheet is representative of initial production runs. These values may be revised at anytime without notice as additional test data becomes available.

DURA♦SKRIM® N60B is a flexible geomembrane, reinforced with a closely knit 9x9 weft inserted polyester scrim fully encapsulated between two layers of highly UV stabilized linear low density polyethylene. Exceptional toughness, high tensile and puncture strength is achieved with the combination of premium high strength LLDPE and dense scrim reinforcement. A highly stabilized formulation consisting of antioxidants, UV stabilizers and carbon black provide excellent protection for long-term exposed or barrier applications.



Scan QR Code to download technical data sheets.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. VIAFLEX MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at [www.viaflex.com](http://www.viaflex.com)

VIAFLEX  
821 W Algonquin St Sioux Falls, SD 57104  
Ph: (605) 335-0174 • TF: (800) 635-3456

© 2023 VIAFLEX, INC. All rights reserved.

sales@viaflex.com  
www.viaflex.com



021618 EFD 1355