

# HYDRALINE™ LL50

LINEAR LOW DENSITY POLYETHYLENE – LAYFLAT – MEETS GRI-GM17



## PRODUCT DESCRIPTION

Linear low density polyethylene (LLDPE) geomembranes are manufactured with high quality resins providing exceptional elongation, multiaxial stress resistance, and flexibility. HydraLine™ LL50 can be easily heat sealed with hot wedge or extrusion welding technologies.

HydraLine™ LL50 features include good resistance to stress cracking, chemical resistance, and UV stable. It is available in black, white and custom colors with minimum quantities. It is also available in textured versions to enhance friction angles in contact with soil or geosynthetic layers.

## PRODUCT USE

HydraLine™ LL-Series is a very flexible geomembrane with high tensile strength, UV stability and conforms well to various surfaces, which performs well in water and waste water applications for commercial and municipal projects, landfill cells, man-made ponds and many other systems.

HydraLine™ LL-Series meets the physical property values as stated in GRI test method GM17.

## SIZE & PACKAGING

HydraLine™ LL50 is shipped to job sites in large master rolls tightly rolled on to a heavy core and deployed by on site equipment. Seaming by certified installation technicians occurs in the field by heat fusion welding.



Tank Liner

## PRODUCT

## PART #

HydraLine™ ..... LL50B

HydraLine™ ..... LL50W

## APPLICATIONS

- |                          |                        |
|--------------------------|------------------------|
| Decorative Ponds & Lakes | Vapor Barriers         |
| Landfill Liner & Caps    | Greens & Bunker Liners |
| Golf Course Ponds        | Irrigation Reservoirs  |
| Landfill Caps            | Containment Pits       |
| Pond & Lake Liners       | Mining Heap Leach Pads |
| Drop-In Tank Liners      | Secondary Containment  |



# HYDRALINE™ LL50

LINEAR LOW DENSITY POLYETHYLENE

		HYDRALINE™ LL50			
		IMPERIAL		METRIC	
PROPERTIES	TEST METHOD	TEST VALUE	TESTING FREQUENCY (MINIMUM)	TEST VALUE	TESTING FREQUENCY (MINIMUM)
APPEARANCE	Black, White & Custom Colors Available				
THICKNESS - (MIN. AVG.)	ASTM D5199	50 Mils	Per roll	1.25 mm	Per roll
DENSITY (MAXIMUM)	ASTM D1505/ ASTM D792	0.939 g/cc	200,000 lb	0.939 g/cc	90,000 kg
TENSILE PROPERTIES (MIN. AVG.) <sup>1</sup> - BREAK STRENGTH - BREAK ELONGATION	ASTM D6693 Type IV	190 lb/in 800 %	20,000 lb	33 N/mm 800 %	9,000 kg
2% MODULUS - (MAX)	ASTM D5323	3000 lb/in	per formulation	520 N/mm	per formulation
TEAR RESISTANCE (MIN. AGE.)	ASTM D1004	27 lb	45,000 lb	120 N	20,000 kg
PUNCTURE RESISTANCE (MIN. AVG.)	ASTM D4833	70 lb	45,000 lb	310 N	20,000 kg
CARBON BLACK CONTENT (RANGE) <sup>1</sup>	ASTM D4218	2.0-3.0 %	45,000 lb	2.0-3.0 %	20,000 kg
CARBON BLACK DISPERSION <sup>1</sup>	ASTM D5596	pass	45,000 lb	pass	20,000 kg

<sup>1</sup> See reference notations for the listed test methods located in the Geosynthetics Research Institute: GRI-GM17 Standard Specification.



Linear low density polyethylene (LLDPE) geomembranes are manufactured with high quality resins providing exceptional elongation, multiaxial stress resistance, and flexibility. HydraLine™ LL50 can be easily heat sealed with hot wedge or extrusion welding technologies.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. VIAFLEX MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at [www.viaflex.com](http://www.viaflex.com)

## VIAFLEX, INC.

821 W Algonquin Street Sioux Falls, SD 57104  
Ph: +1 (605) 335-0174 • TF: +1 (800) 635-3456  
© 2022 VIAFLEX, INC. All rights reserved.

[sales@viaflex.com](mailto:sales@viaflex.com)  
[www.viaflex.com](http://www.viaflex.com)



27-0097 09/22