

HYDRALINE™ LL60

LINEAR LOW DENSITY POLYETHYLENE

		HYDRALINE™ LL60			
		IMPERIAL		METRIC	
PROPERTIES	TEST METHOD	TEST VALUE	TESTING FREQUENCY (MINIMUM)	TEST VALUE	TESTING FREQUENCY (MINIMUM)
APPEARANCE	Black, White & Custom Colors Available				
THICKNESS - (MIN. AVG.)	ASTM D5199	60 Mils	Per roll	1.50 mm	Per roll
DENSITY (MAXIMUM)	ASTM D1505/ ASTM D792	0.939 g/cc	200,000 lb	0.939 g/cc	90,000 kg
TENSILE PROPERTIES (MIN. AVG.) ¹ - BREAK STRENGTH - BREAK ELONGATION	ASTM D6693 Type IV	228 lb/in 800 %	20,000 lb	40 N/mm 800 %	9,000 kg
2% MODULUS - (MAX)	ASTM D5323	3600 lb/in	per formulation	630 N/mm	per formulation
TEAR RESISTANCE (MIN. AGE.)	ASTM D1004	33 lb	45,000 lb	140 N	20,000 kg
PUNCTURE RESISTANCE (MIN. AVG.)	ASTM D4833	84 lb	45,000 lb	374 N	20,000 kg
CARBON BLACK CONTENT (RANGE) ¹	ASTM D4218	2.0-3.0 %	45,000 lb	2.0-3.0 %	20,000 kg
CARBON BLACK DISPERSION ¹	ASTM D5596	pass	45,000 lb	pass	20,000 kg

¹ See reference notations for the listed test methods located in the Geosynthetics Research Institute; GRI-GM17 Standard Specification.



Linear low density polyethylene (LLDPE) geomembranes are manufactured with high quality resins providing exceptional elongation, multiaxial stress resistance, and flexibility. HydraLine™ LL60 can be easily heat sealed with hot wedge or extrusion welding technologies.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. VIAFLEX MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.viaflex.com

VIAFLEX, INC.

821 W Algonquin Street Sioux Falls, SD 57104
Ph: +1 (605) 335-0174 • TF: +1 (800) 635-3456
© 2022 VIAFLEX, INC. All rights reserved.

sales@viaflex.com
www.viaflex.com



27-0108 09/22