
## DURA\*SKRIM® R12BV





## PRODUCT DESCRIPTION

DURA SKRIM® R12BV consists of two sheets of high-strength virgin polyethylene film laminated together with a third layer of molten polyethylene. The black outer layers contain carbon black to enhance outdoor life. A heavy-duty scrim reinforcement placed between these plies greatly enhances tear and puncture resistance and increases service life.



DURA SKRIM® R12BV is reinforced with a high strength scrim reinforcement laid in a diagonal pattern spaced 3/8" apart for uniform tear resistance in both machine and transverse directions with an additional machine direction scrim every 3" across the width for increased stability.

## **PRODUCT USE**


DURA SKRIM® R12BV is used in more demanding applications requiring high tear resistance. It is designed to withstand longer term outdoor applications requiring up to 5 years of exposure or more depending upon geographical location.

DURA SKRIM® R12BV are designed to meet the requirements of the Geosynthetics Research Institute; GRI-GM22 Standard Specification.

#### **SIZE & PACKAGING**

DURA♦SKRIM® R12BV is available in a variety of widths and panels up to 120,000 square feet. All panels are manufactured in a quality controlled environment and are accordion folded and tightly rolled on a heavy-duty core for ease of handling and time-saving installation.





Temporary Rain Shed Cover

## PRODUCT

PART #

DURA♦SKRIM.....

R12R\/

#### **APPLICATIONS**

Daily Landfill Covers Remediation Covers or Liners

Interim Landfill Covers Cargo Coverings

Temporary Rainshed Covers Outdoor Covers

# **DURA\*SKRIM®** R12BV

#### FOUR-LAYER REINFORCED EXTRUSION LAMINATE - MEETS GRI-GM22

		DURA◆SKRIM R12BV				
		IMPERIAL		METRIC		
PROPERTIES	TEST METHOD	MINIMUM	TYPICAL	MINIMUM	TYPICAL	
Appearance		Black/Black				
THICKNESS	ASTM D5199	10 Mil Average	12 Mil Nominal	0.25 mm Average	0.30 mm Nominal	
WEIGHT	ASTM D751	53 lbs/MSF	57 lbs/MSF	259 g/m²	278 g/m²	
Construction		Extrusion laminated with scrim reinforcement				
<sup>2</sup> Grab Tensile	ASTM D7004	80 lbs	100 lbs	356 N	445 N	
<sup>2</sup> Grab Tensile Elongation	ASTM D7004	15 %	17 %	15 %	17 %	
<sup>2</sup> 1" Tensile Strength	ASTM D7003	52 lbs/in	74 lbs/in	91 N/cm	130 N/cm	
<sup>2</sup> Elongation at Film Break	ASTM D7003	100 %	600 %	100 %	600 %	
<sup>3</sup> TONGUE TEAR	ASTM D5884	40 lbs	46 lbs	178 N	205 N	
CBR Puncture Resistance	ASTM D6241	220 lbs	265 lbs	979 N	1179 N	
Mullen Burst	ASTM D751	85 psi	100 psi	586 kPa	690 kPa	
HIGH PRESSURE OIT	ASTM D5885	1000 min	2200 min	1000 min	2200 min	
WVTR	ASTM E96	N/A	0.010 grains/ft <sup>2</sup> •hr	N/A	0.167 g/m <sup>2</sup> •day	
Perm	ASTM E96	N/A	0.023 Perms	N/A	0.015 g/m²•day•mm Hg	
Hydraulic Conductivity	ASTM E96	1.85x10 <sup>-10</sup> cm/sec				
UV RESISTANCE	GRI GM22	> 80% retained / no cracking				
MAXIMUM STATIC USE TEMPERATURE		180° F		82'	82° C	
MINIMUM STATIC USE TEMPERATURE		-70° F		-57° C		

<sup>&</sup>lt;sup>2</sup> Tests are an average of primary reinforcement directions.



DURA SKRIM® R12BV consists of two sheets of high-strength virgin polyethylene film laminated together with a third layer of molten polyethylene. The black outer layers contain carbon black to enhance outdoor life. A heavy-duty scrim reinforcement placed between these plies greatly enhances tear and puncture resistance and increases service life. DURA SKRIM® R12BV is reinforced with a high strength scrim reinforcement laid in a diagonal pattern spaced 3/8" apart for uniform tear resistance in both machine and transverse directions with an additional machine direction scrim every 3" across the width for increased stability.



Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. VIAFLEX MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.viaflex.com

#### VIAFLEX, INC.



<sup>&</sup>lt;sup>3</sup> Tests are an average of machine and transverse directions.