

PRODUCT DESCRIPTION

VaporBlock® Plus™ is a seven-layer co-extruded barrier made using high quality virgin-grade polyethylene and EVOH resins to provide unmatched impact strength as well as superior resistance to gas and moisture transmission. VaporBlock® Plus™ 20 is more than 100 times less permeable than typical high-performance polyethylene vapor retarders against Methane, Radon, and other harmful VOCs. Tested and verified for unsurpassed protection against BTEX, HS, TCE, PCE, methane, radon, other toxic chemicals and odors.

VaporBlock® Plus™ 20 multi-layer gas barrier is manufactured with the latest EVOH barrier technology to mitigate hazardous vapor intrusion from damaging indoor air quality, and the safety and health of building occupants. VBP20 is one of the most effective underslab gas barriers in the building industry today far exceeding ASTM E-1745 (Plastic Water Vapor Retarders Used in Contact with Soil or Granular Fill Under Concrete Slabs) Class A, B and C requirements. Available in a 20 (Class A) mil thicknesses designed to meet the most stringent requirements. VaporBlock® Plus™ 20 is produced within the strict guidelines of our ISO 9001 Certified Management System.

PRODUCT USE

VaporBlock® Plus™ 20 resists gas and moisture migration into the building envelop when properly installed to provide protection from toxic/harmful chemicals. It can be installed as part of a passive or active control system extending across the entire building including floors, walls and crawl spaces. When installed as a passive system it is recommended to also include a ventilated system with sump(s) that could be converted to an active control system with properly designed ventilation fans.

VaporBlock® Plus™ 20 works to protect your flooring and other moisture-sensitive furnishings in the building's interior from moisture and water vapor migration, greatly reducing condensation, mold and degradation.

SIZE & PACKAGING

VaporBlock® Plus™ 20 is available in 10' x 150' rolls to maximize coverage. All rolls are folded on heavy-duty cores for ease in handling and installation. Other custom sizes with factory welded seams are available based on minimum volume requirements. Installation instructions and ASTM E-1745 classifications accompany each roll.



Under-Slab Vapor/Gas Retarder

PRODUCT

PART

VaporBlock® Plus™ 20 VBP20

APPLICATIONS

- | | |
|---------------------|--------------------------------|
| Radon Barrier | Vapor Intrusion Barrier |
| Methane Barrier | Under-Slab Vapor Retarder |
| VOC Barrier | Foundation Wall Vapor Retarder |
| Brownfields Barrier | |



VAPORBLOCK® PLUS™ VBP20

UNDER-SLAB VAPOR / GAS BARRIER

		VAPORBLOCK® PLUS™ 20	
PROPERTIES	TEST METHOD	IMPERIAL	METRIC
APPEARANCE		White/Gold	
THICKNESS, NOMINAL		20 mil	0.51 mm
WEIGHT		102 lbs/MSF	498 g/m ²
CLASSIFICATION	ASTM E 1745	CLASS A, B & C	
³ TENSILE STRENGTH	ASTM E 154 Section 9 (D-882)	58 lbf	102 N
IMPACT RESISTANCE	ASTM D 1709	2600 g	
PERMEANCE (NEW MATERIAL)	ASTM E 154 Section 7 ASTM E 96 Procedure B	0.0098 Perms grains/(ft ² ·hr·in·Hg)	0.0064 Perms g/(24hr·m ² ·mm Hg)
PERMEANCE (AFTER CONDITIONING) (SAME MEASUREMENT AS ABOVE PERMEANCE)	ASTM E 154 Section 8, E96 Section 11, E96 Section 12, E96 Section 13, E96	0.0079 0.0079 0.0097 0.0113	0.0052 0.0052 0.0064 0.0074
WVTR	ASTM E 96 Procedure B	0.0040 grains/hr·ft ²	0.0028 gm/hr·m ²
BENZENE PERMEANCE	See Note ⁶	1.13 x 10 ⁻¹⁰ m ² /sec or 3.62 x 10 ⁻¹³ m/s	
TOLUENE PERMEANCE	See Note ⁶	1.57 x 10 ⁻¹⁰ m ² /sec or 1.46 x 10 ⁻¹³ m/s	
ETHYLBENZENE PERMEANCE	See Note ⁶	1.23 x 10 ⁻¹⁰ m ² /sec or 3.34 x 10 ⁻¹⁴ m/s	
M & P-XYLENES PERMEANCE	See Note ⁶	1.17 x 10 ⁻¹⁰ m ² /sec or 3.81 x 10 ⁻¹⁴ m/s	
O-XYLENE PERMEANCE	See Note ⁶	1.10 x 10 ⁻¹⁰ m ² /sec or 3.43 x 10 ⁻¹⁴ m/s	
HYDROGEN SULFIDE	See Note ⁹	1.92E ⁻⁰⁹ m/s	
TRICHLOROETHYLENE (TCE)	See Note ⁶	7.66 x 10 ⁻¹¹ m ² /sec or 1.05 x 10 ⁻¹⁴ m/s	
PERCHLOROETHYLENE (PCE)	See Note ⁶	7.22 x 10 ⁻¹¹ m ² /sec or 1.04 x 10 ⁻¹⁴ m/s	
RADON DIFFUSION COEFFICIENT	K124/02/95	< 1.1 x 10 ⁻¹³ m ² /s	
METHANE PERMEANCE	ASTM D 1434	3.68E ⁻¹² m/s Gas Transmission Rate (GTR): 0.32 mL/m ² ·day·atm	
MAXIMUM STATIC USE TEMPERATURE		180° F	82° C
MINIMUM STATIC USE TEMPERATURE		- 70° F	- 57° C

³ Tests are an average of machine and transverse directions.

⁵ Raven Industries performs seam testing at 20° per minute.

⁶ Aqueous Phase Film Permeance.

Permeation of Volatile Organic Compounds through EVOH Thin Film Membranes and Coextruded LLDPE/EVOH/LLDPE Geomembranes, McWatters and Rowe, Journal of Geotechnical and Geoenvironmental Engineering © ASCE/September 2015. (Permeation is the Permeation Coefficient adjusted to actual film thickness - calculated at 1 kg/m³)

The study used to determine PCE and TCE is titled: Evaluation of diffusion of PCE & TCE through high performance geomembranes by Di Battista and Rowe, Queens University 8 Feb 2018.

⁹ The study used to determine diffusion coefficients is titled: Hydrogen Sulfide (H₂S) Transport through Simulated Interim Covers with Conventional and Co-Extruded Ethylene-Vinyl Alcohol (EVOH) Geomembranes.

VaporBlock® Plus™ Placement

All instructions on architectural or structural drawings should be reviewed and followed.

Detailed installation instructions accompany each roll of VaporBlock® Plus™ and can also be located at www.ravenefd.com.

ASTM E-1643 also provides general installation information for vapor retarders.

VaporBlock® Plus™
UNDERSLAB VAPOR RETARDER / GAS BARRIER

VaporBlock® Plus™ is a seven-layer co-extruded barrier made using high quality virgin-grade polyethylene and EVOH resins to provide unmatched impact strength as well as superior resistance to gas and moisture transmission.



Scan QR Code to
download technical
data sheets.

Note: To the best of our knowledge, unless otherwise stated, these are typical property values and are intended as guides only, not as specification limits. Chemical resistance, odor transmission, longevity as well as other performance criteria is not implied or given and actual testing must be performed for applicability in specific applications and/or conditions. VIAFLEX MAKES NO WARRANTIES AS TO THE FITNESS FOR A SPECIFIC USE OR MERCHANTABILITY OF PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations and disclaims all liability for resulting loss or damage. Limited Warranty available at www.viaflex.com

VIAFLEX, INC.

821 W Algonquin Street Sioux Falls, SD 57104
Ph: +1 (605) 335-0174 • TF: +1 (800) 635-3456
© 2022 VIAFLEX, INC. All rights reserved.

sales@viaflex.com
www.viaflex.com

Viaflex

27-0123 09/22